

# MATERIAL SAFETY DATA SHEET

## INTERMIX SYSTEM

**SECTION 1 - MANUFACTURER**

**Manufacturer:** **PRO-SPRAY**  
*An Alco Industries Company*  
 600 Nova Drive SE  
 Massillon, Ohio 44646  
 Phone: 330-830-6000  
 Fax: 330-830-6005

**FOR CHEMICAL EMERGENCY**

CHEMTREC: 1-800-424-9300  
 CANUTEC: 1-613-996-6666  
 (For Canada Call Collect)

**Hazardous Materials Information:** See Section 10

**DOT Shipping Name:** Paint, 3 UN1263 PG III  
**OSHA Hazard Class:** Flammable Liquid

**SECTION 2 – HAZARDOUS INGREDIENTS** (see section 10)

HAZARDOUS INGREDIENT	EMERG. PLAN*	NOTE	CAS NO	ACGIH TLV ppm	OSHA PEL ppm	OSHA STEL **ppm	HMIS * H-F-R	FLASH POINT T.C.C./F	VAPOR PRESSURE mm/Hg.
1,2,4 TRIMETHYL BENZENE	YES		95-63-6	25	25	N/E		130	2.03 @77°F
2,4, PENTANEDIONE	YES		123-54-6	20	20		3-3-1	96	6.8 @ 68°F
2-BUTOXYETHYL ACETATE	NO		112-07-2	N/E	N/E	N/E	2-2-0	160	0.2 @ 68°F
ACETONE	YES		67-64-1	750	750	1000	1-3-0	<-1.0	182 @ 68°F
ACRYLIC POLYMER A	NO		N/A	N/E	N/E	N/E	N/A	N/A	N/A
ALUMINIUM HYDROXIDE	NO		21645-51-2	N/E	N/E		1-0-0	N/A	N/A
ALUMINIUM OXIDE	NO		1344-28-1	10 (mg/m <sup>3</sup> ) inhalable total particulate matter	Alpha alumina 5 (mg/m <sup>3</sup> ) respirable fraction	N/E	1-0-0	N/A	N/A
ALUMINUM	NO		7429-90-5	10	5	N/E	N/E	N/A	N/A
AMORPHOUS SILICA	NO		7631-86-9	10	5	N/E	N/A	N/A	N/A
AMORPHOUS SILICON DIOXIDE	NO		112945-52-5	10 (mg/m <sup>3</sup> )	6 (mg/m <sup>3</sup> )	N/E	N/A	N/A	N/A
BUTYL BENZYL PHTHALATE	YES		85-68-7	5 (mg/m <sup>3</sup> ) TWA	5 (mg/m <sup>3</sup> ) TWA	N/A	1-1-0	235	N/E
C.I PIG YELLOW 34 (LEAD SULFOCHROMATE)	YES	3	1344-37-2	0.05 (mg/m <sup>3</sup> )	0.012 (mg/m <sup>3</sup> )		2-2-0	N/A	N/A
C.I PIGMENT BLUE 15	NO		68987-63-3	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIGMENT BROWN 25	NO		6992-11-6	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIGMENT GREEN 7	NO		1328-53-6	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIGMENT YELLOW	NO		15680-42-9	5	10	N/E	N/E	N/A	N/A
C.I PIGMENT YELLOW 42	NO		51274-00-1	5	10	N/E	N/E	N/A	N/A
C.I PIGMENT YELLOW 184 (BISMUTH VANADIUM TETRAOXIDE)	NO		14059-33-7	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIGMENT YELLOW 110	NO		106276-80-6	5	10	N/E	N/E	N/A	N/A
C.I. PIG RED 104 (LEAD MOLBDATE/CHROMATE/SULFATE)	YES	3	12656-85-8	0.05 (mg/m <sup>3</sup> )	0.012 (mg/m <sup>3</sup> )		2-2-0	N/A	N/A
C.I PIGMENT RED 175	NO		6985-92-8	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIGMENT RED 179	NO		5521-31-3	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIGMENT RED 254	NO		84632-65-5	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIGMENT RED 224	NO		128-69-8	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIGMENT QUINACRIDONE RED	NO		1047-16-1	N/E	N/E	N/E	N/E	N/A	N/A
CALCIUM CARBONATE	NO		471-34-1	N/E	N/E	N/E	N/E	N/A	N/A
CARBAZOLE VIOLET	NO		6358-30-1	N/E	N/E	N/E	N/E	N/A	N/A
CARBON BLACK	NO		1333-86-4	3.5 (mg/m <sup>3</sup> )	3.5 (mg/m <sup>3</sup> )	N/E	N/A	N/A	N/A
GRAPHITE	NO		7782-42-5	N/E	N/E	N/E	N/E	N/A	N/A
CELLULOSE ACETATE BUTYRATE	NO		9004-36-8	N/E	N/E	N/E	N/E	N/A	N/A
CHROMIUM HYDROXIDE	NO		1308-14-1	N/E	N/E	N/E	N/E	N/A	N/A
DIISOBUTYL KETONE	NO		108-83-8	25	25	N/E	2-2-0	120	1.7 @ 68°F
ETHYL 3-ETHOXY PROPIONATE	YES		763-69-9	N/E	N/E	100	1-2-0	136	1.5 @ 68°F
ETHYL ACETATE	YES		141-78-6	400	400	N/E	1-3-0	24	86 @ 68°F
ETHYL BENZENE	NO	1	100-41-4	100	100	150	2-3-0	77	7.1 @ 68°F
ETHYLENE GLYCOL N-BUTYL ETHER	NO		111-76-2	N/E	N/E		1-2-0	165	.88 @77°F
FORMALDEHYDE	YES		50-00-0	0.3	0.75	2	3-2-0	N/E	N/E
HYDROPHOBIC FUMED SILICA TREATED WITH DIMETHYLDICHLOROSILANE	NO		68611-44-9	N/E	N/E	N/E		N/A	N/A
HYDROXY ACRYLIC RESIN A	NO		N/A	N/E	N/E	N/E	N/A	N/A	N/A

HYDROXY ACRYLIC RESIN B	NO		N/A	N/E	N/E	N/E	N/A	N/A	N/A
HYDROXY ACRYLIC RESIN C	NO		N/A	N/E	N/E	N/E	N/A	N/A	N/A
INDANTHRONE BLUE	NO		81-77-6	N/E	N/E	N/E	N/E	N/A	N/A
IRON HYDROXIDE OXIDE	NO		20344-49-4	10 (mg/m3)	15 (mg/m3)		1-0-0	N/A	N/A
IRON OXIDE	NO		1309-37-1	5	10	N/E	N/E	N/A	N/A
ISOBUTYL ACETATE	NO		110-19-0	150	150	187	1-3-0	62	14.8 @ 68°F
ISOBUTYL ALCOHOL	NO		78-83-1	N/E	N/E		2-2-0	85	8.8 @ 68°F
ISOPROPYL ALCOHOL	YES		67-63-0	400	400	500	1-3-0	53	32 @ 68°F
MAGNESIUM FLUORIDE MIXTURE	NO		7783-40-6	2.5	2.5	N/E	2-0-0	N/A	N/A
METHYL AMYL KETONE	NO		110-43-0	50	100	N/E	1-2-0	102	2.1 @ 68°F
METHYL ETHYL KETONE	YES		78-93-3	200	200	300	3-3-0	16	85 @ 68°F
METHYL ISOAMYL KETONE	NO		110-12-3	50	100		2-3-0		4.5@25°C
METHYL ISOBUTYL KETONE	YES		108-10-1	50	50	75	2-3-0	60	16 @ 68°F
METHYL PROPYL KETONE	NO		107-87-9	200	200	250	2-3-0	46	27 @ 68°F
MICA (MINERAL)	NO		12001-26-2	3	3	3	N/A	N/A	N/A
MINERAL SPIRITS	NO		8032-32-4	100	100	100	1-2-0	100	<1 @ 68°F
MONOAZO ORANGE	NO		12236-62-3	N/E	N/E	N/E	N/E	N/A	N/A
NAPHTHA (PETROLEUM), HYDROTREATED HEAVY	NO		64742-48-9	400 (8-hr TWA) (for petroleum naphtha)	N/E	N/E	N/E	102-128	<10
N-BUTYL ACETATE	YES		123-86-4	150	150	200	2-3-0	81	10 @ 68°F
N-BUTYL ALCOHOL	YES		71-36-3	50	50	N/E	2-3-0	97	5.5 @ 68°F
N-HEPTANE	NO		142-82-5	400	400		1-3-0	20	60 @77°F
NYLON	NO		25038-74-8	N/E	N/E	N/E	N/A	N/A	N/A
PARACHLOROBENZOTRIFLUORIDE (PCBTF)	NO		98-56-6	N/E	N/E	N/E	1-2-1	109	5.3 @ 68F
PETROLEUM NAPHTHA	NO		8032-32-4	300	300	N/E	2-3-0		3.4 @ 68°F
PTHALOCYANINE BLUE	NO		147-14-8	N/E	N/E	N/E	N/E	N/A	N/A
POLYESTER RESIN A	NO		N/A	N/E	N/E	N/E	N/A	N/A	N/A
POLYESTER RESIN B	NO		N/A	N/E	N/E	N/E	N/A	N/A	N/A
POLYESTER RESIN C	NO		N/A	N/E	N/E	N/E	N/A	N/A	N/A
POLYESTER RESIN F	NO		N/A	N/E	N/E	N/E	N/A	N/A	N/A
PROPYLENE GLYCOL MONOMETHYL ETHER	YES		107-98-2	100	100		2-3-0	94 OPEN CUP	11 @77°F
PROPYLENE GLYCOL MONOMETHYL ETHER ACETATE	NO		108-65-6	N/E	N/E	N/E	2-3-0	114 SETA CLOSED	2.4 @ 68°F
PROPYLENE GLYCOL N-PROPYL ETHER	NO		1569-01-3	N/E	N/E	N/E	2-2-0	118.4	1.7 @ 68°F
QUINACRIDONE	NO		1047-16-1	N/E	N/E	N/E	N/E	N/A	N/A
SILICA	NO		68611-44-9	10 (mg/m3)	6 (mg/m3)	N/E	1-0-0	N/A	N/A
SYNTHETIC AMORPHOUS SILICA	NO		112926-00-8	10 (mg/m3)	6 (mg/m3)	N/E	1-0-0	N/A	N/A
SOLVENT NAPHTHA (PETROLEUM), LIGHT AROMATIC	NO		64742-95-6	100	100	N/E	2-3-0	110	4 @ 68°F
TIN OXIDE	YES		18282-10-5	2 (mg/m3)	2 (mg/m3) TWA	N/A	2-2-0	N/A	N/A
TITANIUM DIOXIDE	NO		13463-67-7	N/E	N/E		0-0-0	N/A	N/A
TOLUENE	YES	2	108-88-3	50	100	150	2-3-0	45	47 @ 68°F
VM&P NAPHTHA	NO		64742-89-8	N/E	N/E		1-3-0	18	38 @ 68°F
XYLENE	YES	1	1330-20-7	100	100	150	2-3-0	80	9.5 @ 68°F
YELLOW BENZIMIDAZOLONE	NO		68134-22-5	N/E	N/E	N/E	N/A	N/A	N/A
ZIRCONIUM OXIDE	NO		1314-23-4	5 (mg/m3) as Zr	5 (mg/m3) as Zr	10 (mg/m3) as Zr	1-0-0	N/A	N/A

Key: ACGIH = American Conference of Government Industrial Hygienists; OSHA = Occupational Safety and Health Administration; TLV = Threshold Limit Value; TWA = Time Weighted Average; PEL = Permissible Exposure Limit (1989 Vacated Values); HMIS = Hazardous Materials Identification System (Rating System 0=Minimal, 1=Slight, 2=Moderate, 3=Serious, 4=Severe, \*=Chronic effects); (S = Potential Skin Absorption; R = Respirable dust). N/E = Not Established.

### SECTION 3 – PHYSICAL DATA

**Evaporation rate:** Less than ether

**Solubility in water:** 0.1%

**Percentage volatile by weight:** 21.00 – 83.0%

**Gallon weight:** 7.75 – 13.00 lb/gallon

**Vapor density:** Heavier than air

**Percent volatile by volume:** 35% - 86.4%

**Boiling range:** 54 °C - 245°C/129°F-473°F

### SECTION 4 – FIRE & EXPLOSION DATA

**Flash point (closed cup):** See section 10 for exact values

**Flammable limits:** 0.8% - 19.9%

**Extinguishing media:** Water spray, foam, carbon dioxide, and dry chemical.

**Special fire fighting procedures:** Full protective equipment, including self-contained breathing apparatus is recommended. Water from fog nozzles may be used to cool closed containers to prevent pressure build up.

**Unusual fire & explosion hazards:** When heated above the flash point, emits flammable vapors which, when mixed with air, can burn or be explosive. Fine mists or sprays may be flammable at temperatures below the flash point.

## **SECTION 5 – HEALTH HAZARD DATA**

### **General Effects:**

**Ingestion:** Gastro-intestinal distress. In the unlikely event of ingestion, call a physician immediately and have the names of the ingredients available.

**Inhalation:** May cause nose and throat irritation. May cause nervous system depression characterized by the following progressive steps: Headache, dizziness, nausea, staggering gait, confusion, and/or unconsciousness. **Toluene** has been found by the state of California to cause birth defects and other reproductive harm. **Propylene glycol Monomethyl ether acetate** and **n-Butyl alcohol** may cause moderate eye burning and can be absorbed through the skin in harmful amounts. Laboratory studies with rats have shown that petroleum distillates cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown significant increases of kidney damage or kidney or liver tumors. Extremely high concentration of n-butyl acetate has caused blood changes and weakness in laboratory animals. Repeated extremely high exposures of laboratory animals to **Ethyl acetate** resulted in secondary anemia with and increase in white blood cells, fatty degeneration, cloudy swelling, and an excess of blood in various organs. **Dibasic ester** inhalation overexposure in rats has shown mild injury to the olfactory region of the nose. **Ethylene glycol monobutyl ether acetate** can be absorbed through the skin in harmful amounts. In studies in laboratory animals has produced damage to red blood cells and kidneys. Reports have associated repeated and prolonged overexposure to solvents with permanent brain and nervous system damage. If affected by inhalation of vapor or spray mist, remove to fresh air. If breathing difficulty persists, or occurs later, consult a physician.

Skin or eye contact: Repeated or prolonged liquid contact may cause skin irritation with discomfort and dermatitis. In case of eye contact, immediately flush with plenty of water for at least 15 minutes; and call a physician. In case of skin contact, wash with soap and water. If irritation occurs, contact a physician.

**Skin or eye contact:** May cause irritation or burning of the eyes. Repeated or prolongs liquid contact may cause skin irritation with discomfort and dermatitis. In case of eye contact, immediately flush with plenty of water for at least 15 minutes; call a physician. In case of skin contact, wash with soap and water. If irritation occurs, contact a doctor.

### **Special Effects:**

**Aromatic hydrocarbon A, B; VM&P Naphtha** – laboratory studies with rats have shown that petroleum distillates cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

**Butyl acetate** – may cause abnormal liver function. Tests for embryotoxic activity in animals has been conclusive. Has been toxic to the fetus in laboratory animals at doses that are toxic to the mother.

**Melamine resin** – This chemical is a formaldehyde donor. Formaldehyde is an IARC, NTP or OSHA carcinogen and has shown mutagenic activity in laboratory cell culture tests. Formaldehyde has produced tumors in the nasal passage of laboratory animals when exposed to high concentrations for a two-year period. Epidemiology studies conducted to date have not found evidence of formaldehyde related tumor induction in humans.

**Warning:** This chemical is known to the State of California to cause cancer.

**Methyl ethyl ketone** – High concentrations have caused embryotoxic effects in laboratory animals. Methyl ethyl ketone has been demonstrated to potentiate (i.e., shorten the time of onset) the peripheral neuropathy caused by either n-hexane or methyl n-butyl ketone. MEK by itself has not been demonstrated to cause peripheral neuropathy. Liquid splashes in the eye may result in chemical burns.

**Titanium dioxide** - In a lifetime inhalation test, lung cancers were found in some rats exposed to 250-mg/m<sup>3</sup> respirable titanium dust. Analysis of the titanium dioxide concentrations in the rat's lungs showed that the lung clearance mechanism was overwhelmed and that the results at the massive 250-mg/m<sup>3</sup> levels are not relevant to the workplace.

**Toluene** – Recurrent overexposure may result in liver and kidney injury. High airborne levels have produced irregular heartbeat in animals and occasional palpitations in humans. Rats exposed to very high airborne levels have exhibited high frequency hearing defects. The significance of this to man is unknown.

**Warning:** This chemical is known to the State of California to cause birth defects or other reproductive harm.

**Xylene** – High concentrations have caused embryotoxic effects in laboratory animals. Recurrent overexposure may result in liver and kidney injury. Can be absorbed through the skin in harmful amounts.

**Formaldehyde** – repeated exposure may cause allergic skin rash, itching, swelling. Causes severe eye irritation. Formaldehyde has produced tumors in the nasal passage of laboratory animals when exposed to high concentrations for a two-year period. Epidemiology studies conducted to date have not found evidence of formaldehyde related tumor induction in humans. May induce pulmonary sensitization or significant irritation of the respiratory airways. Is an IRAC, NTP or OSHA carcinogen? Has shown mutagenic activity in laboratory cell culture tests.

**Warning:** This chemical is known to the State of California to cause cancer.

## **SECTION 6 – REACTIVITY DATA**

**Stability:** Stable

**Incompatibility (materials to avoid):** None reasonably foreseeable

**Hazardous decomposition products:** CO, CO<sub>2</sub>, smoke

**Hazardous polymerization:** Will not occur

## **SECTION 7 – SPILL OR LEAK PROCEDURES**

**STEPS TO BE TAKEN IN CASE MATERIAL IS RELEASED OR SPILLED:** Provide maximum ventilation. Only personnel equipped with proper respiratory, skin, and eye protection should be permitted in the area. Remove all sources of ignition. Take up spilled material with sand, vermiculite, or other non-combustible absorbent material and place in clean, empty containers for disposal. Only the spilled material and the absorbent should be placed in this container.

**WASTE DISPOSAL METHOD:** Waste material must be disposed of in accordance with federal, state, provincial, and local environmental control regulations. Empty containers should be recycled or disposed of through an approved waste management facility.

## **SECTION 8 – SPECIAL PRECAUTIONS**

**Precautions to be taken in handling and storing:** Observe label precautions. Keep away from heat, sparks, and flame. Close container after each use. Ground containers when pouring. Wash thoroughly after handling and before eating or smoking. Do not store above 120°F.

**Other precautions:** DO NOT sand, flame cut, braze or weld dry coating without a NIOSH/MSHA approved respirator or appropriate ventilation.

\* Subject to the reporting requirements of section 313 of the Emergency Planning and Community right to know act of 1986 and 40CFR372.

\*\* Short-term exposure limit

Note 1 - Xylene contains 18-20% Ethyl Benzene (CAS# 100-41-4) having a PEL of 100 ppm, TLV of 100 ppm and a STEL of 150 ppm.

Note 2 - Toluene is known to the state of California to cause birth defects or other reproductive harm.

Note 3- This raw material is known to the state of California to cause Cancer and adverse reproductive effects.

N/E - Not established as reported by manufacturer.

**Respiratory:** DO NOT breathe vapors or mists. When this product is used with a pint requiring isocyanate hardener or activator, wear a continuous flow supplied air respirator (NIOSH/MSHA TC-19C approved) when mixing the hardener/activator with the paint, during application and until all vapor and spray

mists are exhausted. DO NOT permit anyone without respirator protection in the painting area. Refer to the hardener/activator label instructions and MSDS for further information. Follow the respirator manufacturer's directions for respirator use.

**Ventilation:** Provide sufficient ventilation in volume and pattern to keep contaminants below applicable OSHA requirements.

**Protective clothing:** Neoprene gloves and coveralls are recommended.

**Eye protection:** Desirable in all industrial situations. Include splashguards or side shields.

## **SECTION 10 – OTHER INFORMATION**

**Section 313 Supplier Notification:** The chemicals listed below with percentages are subject to the reporting requirements of Section 313 of the Emergency Planning and Right-To-Know Act of 1986 and of 40 CFR 372.

~ NFPA ratings for individual products have not been established. The ratings given are the highest rating of any ingredient contained in that product.

**NOTICE:** The data in this Material Safety Data Sheet relate only to the specific material designated herein and do not relate to use in combination with another material or in any process.

### **Product Code: Pro-Spray MB-201-2 PALE WHITE MS TINTER**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Xylene (10%), ethyl benzene, Titanium Dioxide (1-5%)

Gallon Weight:	8.25 lb	Boiling Range:	259-418°F
% Solids by Weight:	41.0	H: 2 F: 3 R: 0	
% Solids by Volume:	33.7	Flash Point:	70°F
V.O.C LE:	4.87 lb gal	OSHA Storage:	1B
V.O.C AP:	4.87 lb gal		

### **Product Code: Pro-Spray MB-203-2 TRANSPARENT BLACK MS TINTER**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Xylene (10%), ethyl benzene, Carbon Black (0.1-1.0%)

Gallon Weight:	8.17 lb	Boiling Range:	259-418°F
% Solids by Weight:	41.1	H: 2 F: 3 R: 0	
% Solids by Volume:	34.5	Flash Point:	70°F
V.O.C LE:	4.81 lb gal	OSHA Storage:	1B
V.O.C AP:	4.81 lb gal		

### **Product Code: Pro-Spray MB-204-3 YELLOW OXIDE MS TINTER**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (10%), Iron Hydroxide Oxide (10-20%)

Gallon Weight:	9.16 lb	Boiling Range:	259-418°F
% Solids by Weight:	53.8	H: 2 F: 3 R: 0	
% Solids by Volume:	42.2	Flash Point:	70°F
V.O.C LE:	4.23 lb gal	OSHA Storage:	1B
V.O.C AP:	4.23 lb gal		

### **Product Code: Pro-Spray MB-205-2 TRACE YELLOW TINTER**

Hydroxy Acrylic Resin B, Hydroxy Acrylic Resin C, N-Butyl Acetate (40-50%), Xylene (1-10%), ethyl benzene (0.5-1%), Propylene glycol monomethyl ether acetate (1-10%), N-Butyl Alcohol (0.1-0.5%), C.I. Pigment Yellow 184 (Bismuth vanadium tetraoxide) (1-5%), Silica (1-5%), Amorphous silicon dioxide (0.1-0.5%).

Gallon Weight:	8.44 lb	Boiling Range:	259-418°F
% Solids by Weight:	48	H: 2 F: 3 R: 0	
% Solids by Volume:	34.1	Flash Point:	70°F
V.O.C LE:	4.84 lb gal	OSHA Storage:	1B
V.O.C AP:	4.84 lb gal		

### **Product Code: Pro-Spray MB-206-3 RED OXIDE MS TINTER**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (10%), Iron Oxide (10-20%)

Gallon Weight:	9.16 lb	Boiling Range:	259-418°F
% Solids by Weight:	53.1	H: 2 F: 3 R: 0	
% Solids by Volume:	41.3	Flash Point:	70°F
V.O.C LE:	4.30 lb gal	OSHA Storage:	1B
V.O.C AP:	4.30 lb gal		

### **Product Code: Pro-Spray MB-207-2 RUSSET MS TINTER**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (10%), Iron Oxide (1-5 %).

Gallon Weight:	8.29 lb	Boiling Range:	259-418°F
% Solids by Weight:	42.3	H: 2 F: 3 R: 0	
% Solids by Volume:	34.9	Flash Point:	70°F
V.O.C LE:	4.78 lb gal	OSHA Storage:	1B
V.O.C AP:	4.78 lb gal		

### **Product Code: Pro-Spray MB-209-2 DEEP BLUE MS TINTER**

Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (10%), Phthalocyanine Blue (0.1-1.0%).

Gallon Weight:	8.24 lb	Boiling Range:	259-418°F
% Solids by Weight:	43.0	H: 2 F: 3 R: 0	
% Solids by Volume:	36.1	Flash Point:	70°F
V.O.C LE:	4.69 lb gal	OSHA Storage:	1B
V.O.C AP:	4.69 lb gal		

**Product Code: Pro-Spray MB-215-2 MEDIUM YELLOW MS TINTER**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (10%), Iron Hydroxide Oxide (0.1-1.0%)

Gallon Weight:	8.18 lb	Boiling Range:	259-418°F
% Solids by Weight:	41.4	H: 2 F: 3 R: 0	
% Solids by Volume:	34.7	Flash Point:	70°F
V.O.C LE:	4.79 lb gal	OSHA Storage:	1B
V.O.C AP:	4.79 lb gal		

**Product Code: Pro-Spray MB-219-2 VIOLET MS TINTER**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (10%), Carbazole Violet (1-5%)

Gallon Weight:	8.25 lb	Boiling Range:	259-418°F
% Solids by Weight:	40.7	H: 2 F: 3 R: 0	
% Solids by Volume:	33.4	Flash Point:	70°F
V.O.C LE:	4.89 lb gal	OSHA Storage:	1B
V.O.C AP:	4.89 lb gal		

**Product Code: Pro-Spray MB-224-2 SUPER RED MS TINTER**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (10%), Ci Red 168

Gallon Weight:	8.35 lb	Boiling Range:	259-418°F
% Solids by Weight:	41.1	H: 2 F: 3 R: 0	
% Solids by Volume:	33.1	Flash Point:	70°F
V.O.C LE:	4.91 lb gal	OSHA Storage:	1B
V.O.C AP:	4.91 lb gal		

**Product Code: Pro-Spray MB-229-3 BLUE LAKE MS TINTER**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (5-10%), Indanthrone Blue (5-10%)

Gallon Weight:	8.39 lb	Boiling Range:	259-418°F
% Solids by Weight:	43.5	H: 2 F: 3 R: 0	
% Solids by Volume:	35.5	Flash Point:	70°F
V.O.C LE:	4.74 lb gal	OSHA Storage:	1B
V.O.C AP:	4.74 lb gal		

**Product Code: Pro-Spray MB-231-3 BLUE BLACK MS TINTER**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (5-10%), Carbon Black (1-5%)

Gallon Weight:	8.27 lb	Boiling Range:	259-418°F
% Solids by Weight:	43.7	H: 2 F: 3 R: 0	
% Solids by Volume:	36.6	Flash Point:	70°F
V.O.C LE:	4.66 lb gal	OSHA Storage:	1B
V.O.C AP:	4.66 lb gal		

**Product Code: Pro-Spray MB-237-2 TONE CONTROLLER**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (5-10%), Synthetic amorphous silica (10-20%)

Gallon Weight:	8.65 lb	Boiling Range:	259-418°F
% Solids by Weight:	50.2	H: 2 F: 3 R: 0	
% Solids by Volume:	41.4	Flash Point:	70°F
V.O.C LE:	4.31 lb gal	OSHA Storage:	1B
V.O.C AP:	4.31 lb gal		

**Product Code: Pro-Spray MB-240-2 TRANSOXIDE RED MS TINTER**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (5-10%), Iron Oxide (10-20%)

Gallon Weight:	9.39 lb	Boiling Range:	259-418°F
% Solids by Weight:	53.3	H: 2 F: 3 R: 0	
% Solids by Volume:	40.3	Flash Point:	70°F
V.O.C LE:	4.38 lb gal	OSHA Storage:	1B
V.O.C AP:	4.38 lb gal		

**Product Code: Pro-Spray MB-251-2 FAST BLUE MS TINTER**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (5-10%) Phthalocyanine Blue (5-10%)

Gallon Weight:	8.38 lb	Boiling Range:	259-418°F
% Solids by Weight:	42.6	H: 2 F: 3 R: 0	
% Solids by Volume:	34.5	Flash Point:	70°F
V.O.C LE:	4.81 lb gal	OSHA Storage:	1B
V.O.C AP:	4.81 lb gal		

**Product Code: Pro-Spray MB-259-2 BURGUNDY MS TINTER**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (5-10%)

Gallon Weight:	8.19 lb	Boiling Range:	259-418°F
% Solids by Weight:	41.3	H: 2 F: 3 R: 0	
% Solids by Volume:	34.6	Flash Point:	70°F
V.O.C LE:	4.81 lb gal	OSHA Storage:	1B
V.O.C AP:	4.81 lb gal		

**Product Code: Pro-Spray MB-265-2 WINE RED MS TINTER**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (5-10%) C.I. Red 175 (10-20%).

Gallon Weight:	8.37 lb	Boiling Range:	259-418°F
% Solids by Weight:	48.2	H: 2 F: 3 R: 0	
% Solids by Volume:	41.0	Flash Point:	70°F
V.O.C LE:	4.34 lb gal	OSHA Storage:	1B
V.O.C AP:	4.34 lb gal		

**Product Code: Pro-Spray MB-272-2 CYAN BLUE MS TINTER**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (5-10%) Phthalocyanine Blue (5-10%)

Gallon Weight:	8.25 lb	Boiling Range:	259-418°F
% Solids by Weight:	42.3	H: 2 F: 3 R: 0	
% Solids by Volume:	35.2	Flash Point:	70°F
V.O.C LE:	4.76 lb gal	OSHA Storage:	1B
V.O.C AP:	4.76 lb gal		

**Product Code: Pro-Spray MB-273 -2 BRONZE GREEN**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (5-10%) Yellow pigment (10-20%).

Gallon Weight:	8.37 lb	Boiling Range:	259-418°F
% Solids by Weight:	45.3	H: 2 F: 3 R: 0	
% Solids by Volume:	37.7	Flash Point:	70°F
V.O.C LE:	4.58 lb gal	OSHA Storage:	1B
V.O.C AP:	4.58 lb gal		

**Product Code: Pro-Spray MB-275-2 STRONG MAROON**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (5-10%), pigment red 179 (5-10%).

Gallon Weight:	8.56 lb	Boiling Range:	259-418°F
% Solids by Weight:	44.4	H: 2 F: 3 R: 0	
% Solids by Volume:	35.2	Flash Point:	70°F
V.O.C LE:	4.76 lb gal	OSHA Storage:	1B
V.O.C AP:	4.76 lb gal		

**Product Code: Pro-Spray MB-276-2 BROWN**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (5-10%), C.I. pigment brown 25 (5-10%).

Gallon Weight:	8.30 lb	Boiling Range:	259-418°F
% Solids by Weight:	46.6	H: 2 F: 3 R: 0	
% Solids by Volume:	39.7	Flash Point:	70°F
V.O.C LE:	4.43 lb gal	OSHA Storage:	1B
V.O.C AP:	4.43 lb gal		

**Product Code: Pro-Spray MB-277-2 FAST MAROON**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (5-10%), pigment quinacridone red (5-10%).

Gallon Weight:	8.40 lb	Boiling Range:	259-418°F
% Solids by Weight:	48.5	H: 2 F: 3 R: 0	
% Solids by Volume:	41.1	Flash Point:	70°F
V.O.C LE:	4.32 lb gal	OSHA Storage:	1B
V.O.C AP:	4.32 lb gal		

**Product Code: Pro-Spray MB-278-2 TRANSOXIDE YELLOW**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (5-10%), C.I pigment yellow 42 (10-20%).

Gallon Weight:	8.99 lb	Boiling Range:	259-418°F
% Solids by Weight:	50.6	H: 2 F: 3 R: 0	
% Solids by Volume:	39.5	Flash Point:	70°F
V.O.C LE:	4.44 lb gal	OSHA Storage:	1B
V.O.C AP:	4.44 lb gal		

**Product Code: Pro-Spray MB-279-2 STRONG YELLOW**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (5-10%), C.I pigment yellow 110 (10-20%)

Gallon Weight:	8.54 lb	Boiling Range:	259-418°F
% Solids by Weight:	41.9	H: 2 F: 3 R: 0	
% Solids by Volume:	32.5	Flash Point:	70°F
V.O.C LE:	4.96 lb gal	OSHA Storage:	1B
V.O.C AP:	4.96 lb gal		

**Product Code: Pro-Spray HB-500-3 H.S. SUPER WHITE**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Xylene (10%), Titanium Dioxide (20-30%), Amorphous silica, aluminium hydroxide.

Gallon Weight:	11.04 lb	Boiling Range:	259-418°F
% Solids by Weight:	63.4	H: 2 F: 3 R: 0	
% Solids by Volume:	44.8	Flash Point:	70°F

V.O.C LE: 4.04 lb gal OSHA Storage: 1B  
V.O.C AP: 4.04 lb gal

**Product Code: Pro-Spray HB-511-2 H.S. CLARET**

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (10%), Quinacridone (5-10%)  
Gallon Weight: 8.46 lb Boiling Range: 259-418°F  
% Solids by Weight: 43.0 H: 2 F: 3 R: 0  
% Solids by Volume: 34.3 Flash Point: 70°F  
V.O.C LE: 4.82 lb gal OSHA Storage: 1B  
V.O.C AP: 4.82 lb gal

**Product Code: Pro-Spray HB-512-2 H.S. LAGOON BLUE**

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, ethyl benzene, NOButyl Acetate, Xylene (10%), C.I Pigment Blue (5-10%)  
Gallon Weight: 8.42 lb Boiling Range: 259-418°F  
% Solids by Weight: 43.1 H: 2 F: 3 R: 0  
% Solids by Volume: 34.8 Flash Point: 70°F  
V.O.C LE: 4.79 lb gal OSHA Storage: 1B  
V.O.C AP: 4.79 lb gal

**Product Code: Pro-Spray HB-520-3 H.S. ORANGE**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Xylene (10%), Amorphous Silicon dioxide (1-5%),  
Ci Pigment Red 104 (30-40%),  
Gallon Weight: 11.87 lb Boiling Range: 259-418°F  
% Solids by Weight: 63.9 H: 2 F: 3 R: 0  
% Solids by Volume: 41.5 Flash Point: 70°F  
V.O.C LE: 4.28 lb gal OSHA Storage: 1B  
V.O.C AP: 4.28 lb gal

**Product Code: Pro-Spray HB-523-2 H.S. BRIGHT YELLOW**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Xylene (5-10%), Lead Chromate-Lead Sulfate (30-40%), Silica, solvent naphtha (petroleum), light aromatic,  
Gallon Weight: 13.00 lb Boiling Range: 259-418°F  
% Solids by Weight: 67.7 H: 2 F: 3 R: 0  
% Solids by Volume: 42.6 Flash Point: 70°F  
V.O.C LE: 4.20 lb gal OSHA Storage: 1B  
V.O.C AP: 4.20 lb gal

**Product Code: Pro-Spray HB-525-2 H.S. SUN YELLOW**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Xylene (5-10%), Lead Chromate-Lead Sulfate (30-40%), Amorphous Silicon dioxide, solvent naphtha (petroleum), light aromatic,  
Gallon Weight: 12.86 lb Boiling Range: 259-418°F  
% Solids by Weight: 68.1 H: 2 F: 3 R: 0  
% Solids by Volume: 43.9 Flash Point: 70°F  
V.O.C LE: 4.10 lb gal OSHA Storage: 1B  
V.O.C AP: 4.10 lb gal

**Product Code: Pro-Spray HB-545-3 H.S. STRONG RED**

Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Xylene (5-10%), Pigment Red 254 (10-20%)  
Gallon Weight: 8.63 lb Boiling Range: 259-418°F  
% Solids by Weight: 49.5 H: 2 F: 3 R: 0  
% Solids by Volume: 40.5 Flash Point: 70°F  
V.O.C LE: 4.36 lb gal OSHA Storage: 1B  
V.O.C AP: 4.36 lb gal

**Product Code: Pro-Spray HB-546-2, HB-546-3 H.S. BLACK**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Carbon Black (1-5%).  
Gallon Weight: 8.37 lb Boiling Range: 259-418°F  
% Solids by Weight: 43.6 H: 2 F: 3 R: 0  
% Solids by Volume: 35.7 Flash Point: 70°F  
V.O.C LE: 4.72 lb gal OSHA Storage: 1B  
V.O.C AP: 4.72 lb gal

**Product Code: Pro-Spray HB-547-2, HB-547-3 H.S. JET BLACK**

Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Xylene (5-10%), Carbon Black (1-5%)  
Gallon Weight: 8.35 lb Boiling Range: 259-418°F  
% Solids by Weight: 41.6 H: 2 F: 3 R: 0  
% Solids by Volume: 33.6 Flash Point: 70°F  
V.O.C LE: 4.87 lb gal OSHA Storage: 1B  
V.O.C AP: 4.87 lb gal

**Product Code: Pro-Spray HB-551-2 H.S. BLUE GREEN**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Xylene (10-20%), C.I Pigment Green 7 (10-20%).  
Gallon Weight: 8.77 lb Boiling Range: 259-418°F  
% Solids by Weight: 44.0 H: 2 F: 3 R: 0  
% Solids by Volume: 33.1 Flash Point: 70°F

V.O.C LE: 4.91 lb gal  
V.O.C AP: 4.91 lb gal

OSHA Storage: 1B

**Product Code: Pro-Spray HB-552-2 H.S. FAST BLUE**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Xylene (5-10%), Phthalocyanine Blue 15 (5-10%)

Gallon Weight: 8.51 lb  
% Solids by Weight: 42.8  
% Solids by Volume: 33.8  
V.O.C LE: 4.86 lb gal  
V.O.C AP: 4.86 lb gal

Boiling Range: 259-418°F  
H: 2 F: 3 R: 0  
Flash Point: 70°F  
OSHA Storage: 1B

**Product Code: Pro-Spray HB-570-2 H.S. BRILLIANT RED**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Xylene (5-10%), C.I. pigment red 254 (1-5%)

Gallon Weight: 8.43 lb  
% Solids by Weight: 47.7  
% Solids by Volume: 40.0  
V.O.C LE: 4.41 lb gal  
V.O.C AP: 4.41 lb gal

Boiling Range: 259-418°F  
H: 2 F: 3 R: 0  
Flash Point: 70°F  
OSHA Storage: 1B

**Product Code: Pro-Spray AB-810-2 H.S. BRIGHT MEDIUM ALUMINIUM**

Polyester resin A, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Propylene glycol monomethyl ether acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%).

Gallon Weight: 8.28 lb  
% Solids by Weight: 33.1  
% Solids by Volume: 25.2  
V.O.C LE: 5.54 lb gal  
V.O.C AP: 5.54 lb gal

Boiling Range: 259-428°F  
H: 2 F: 3 R: 0  
Flash Point: 79°F  
OSHA Storage: 1B

**Product Code: Pro-Spray AB-814-2 H.S. FINE ALUMINIUM**

Polyester resin A, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Propylene glycol monomethyl ether acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%).

Gallon Weight: 8.08 lb  
% Solids by Weight: 29.1  
% Solids by Volume: 22.6  
V.O.C LE: 5.73 lb gal  
V.O.C AP: 5.73 lb gal

Boiling Range: 259-428°F  
H: 2 F: 3 R: 0  
Flash Point: 70°F  
OSHA Storage: 1B

**Product Code: Pro-Spray AB-816-3 H.S. MEDIUM ALUMINIUM**

Polyester resin A, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Propylene glycol monomethyl ether acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%).

Gallon Weight: 8.25 lb  
% Solids by Weight: 31.7  
% Solids by Volume: 23.8  
V.O.C LE: 5.64 lb gal  
V.O.C AP: 5.64 lb gal

Boiling Range: 259-428°F  
H: 2 F: 3 R: 0  
Flash Point: 70°F  
OSHA Storage: 1B

**Product Code: Pro-Spray AB-818-3 H.S. MEDIUM COARSE ALUMINIUM**

Polyester resin A, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Propylene glycol monomethyl ether acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%).

Gallon Weight: 8.29 lb  
% Solids by Weight: 30.7  
% Solids by Volume: 22.4  
V.O.C LE: 5.74 lb gal  
V.O.C AP: 5.74 lb gal

Boiling Range: 259-428°F  
H: 2 F: 3 R: 0  
Flash Point: 70°F  
OSHA Storage: 1B

**Product Code: Pro-Spray AB-821-2 H.S. COARSE ALUMINIUM**

Polyester resin A, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Propylene glycol monomethyl ether acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%).

Gallon Weight: 8.18 lb  
% Solids by Weight: 30.3  
% Solids by Volume: 23.0  
V.O.C LE: 5.70 lb gal  
V.O.C AP: 5.70 lb gal

Boiling Range: 259-428°F  
H: 2 F: 3 R: 0  
Flash Point: 70°F  
OSHA Storage: 1B

**Product Code: Pro-Spray AB-832-2 H.S. VERY COARSE ALUMINIUM**

Polyester resin A, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Propylene glycol monomethyl ether acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%).

Gallon Weight: 8.19 lb  
% Solids by Weight: 30.0  
% Solids by Volume: 22.6  
V.O.C LE: 5.73 lb gal  
V.O.C AP: 5.73 lb gal

Boiling Range: 259-428°F  
H: 2 F: 3 R: 0  
Flash Point: 70°F  
OSHA Storage: 1B

**Product Code: Pro-Spray AB-838-2 H.S. BRIGHT MEDIUM ALUMINIUM**

Polyester resin A, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Propylene glycol monomethyl ether acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%).

Gallon Weight: 8.36 lb  
% Solids by Weight: 31.1

Boiling Range: 259-428°F  
H: 2 F: 3 R: 0

% Solids by Volume:	22.2	Flash Point:	70°F
V.O.C LE:	5.76 lb gal	OSHA Storage:	1B
V.O.C AP:	5.76 lb gal		

**Product Code: Pro-Spray AB-841-2 SHINING COARSE ALUMINIUM**

Polyester resin A, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Propylene glycol monomethyl ether acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%).

Gallon Weight:	8.38 lb	Boiling Range:	259-428°F
% Solids by Weight:	33.1	H: 2 F: 3 R: 0	
% Solids by Volume:	24.3	Flash Point:	70°F
V.O.C LE:	5.60 lb gal	OSHA Storage:	1B
V.O.C AP:	5.60 lb gal		

**Product Code: Pro-Spray AB-842-2 COARSE SILVER DOLLAR ALUMINIUM**

Polyester resin A, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Propylene glycol monomethyl ether acetate, Xylene (12.9%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%), Ethylbenzene (1-10%), N-Butyl Alcohol (1-10%), 1,2,4-Trimethylbenzene (1-10%).

Gallon Weight:	8.06 lb	Boiling Range:	259-428°F
% Solids by Weight:	28.9	H: 2 F: 3 R: 0	
% Solids by Volume:	22.6	Flash Point:	70°F
V.O.C LE:	5.73 lb gal	OSHA Storage:	1B
V.O.C AP:	5.73 lb gal		

**Product Code: Pro-Spray SB-961-2 SLM FINE ALUMINIUM**

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Propylene glycol monomethyl ether acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (1-5%).

Gallon Weight:	8.24 lb	Boiling Range:	259-428°F
% Solids by Weight:	40.6	H: 2 F: 3 R: 0	
% Solids by Volume:	34.1	Flash Point:	70°F
V.O.C LE:	4.89 lb gal	OSHA Storage:	1B
V.O.C AP:	4.89 lb gal		

**Product Code: Pro-Spray SB-962-2 SLM MEDIUM ALUMINIUM**

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Propylene glycol monomethyl ether acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (1-5%).

Gallon Weight:	8.25 lb	Boiling Range:	259-428°F
% Solids by Weight:	40.3	H: 2 F: 3 R: 0	
% Solids by Volume:	33.7	Flash Point:	70°F
V.O.C LE:	4.92 lb gal	OSHA Storage:	1B
V.O.C AP:	4.92 lb gal		

**Product Code: Pro-Spray SB-967-2 SLM COARSE ALUMINIUM**

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Propylene glycol monomethyl ether acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (1-5%).

Gallon Weight:	8.30 lb	Boiling Range:	259-428°F
% Solids by Weight:	40.8	H: 2 F: 3 R: 0	
% Solids by Volume:	33.8	Flash Point:	70°F
V.O.C LE:	4.91 lb gal	OSHA Storage:	1B
V.O.C AP:	4.91 lb gal		

**Product Code: Pro-Spray PB-780-2 PEARL WHITE**

Polyester resin A, N-Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), titanium oxide.

Gallon Weight:	8.48 lb	Boiling Range:	259-368°F
% Solids by Weight:	32.6	H: 2 F: 3 R: 0	
% Solids by Volume:	22.8	Flash Point:	77°F
V.O.C LE:	5.71 lb gal	OSHA Storage:	1B
V.O.C AP:	5.71 lb gal		

**Product Code: Pro-Spray PB-781-2 FINE PEARL WHITE**

Polyester resin A, N-Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), titanium oxide.

Gallon Weight:	8.36 lb	Boiling Range:	259-368°F
% Solids by Weight:	31.5	H: 2 F: 3 R: 0	
% Solids by Volume:	22.6	Flash Point:	70°F
V.O.C LE:	5.73 lb gal	OSHA Storage:	1B
V.O.C AP:	5.73 lb gal		

**Product Code: Pro-Spray PB-782-2 PEARL BLUE**

Polyester resin A, N-Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), titanium oxide.

Gallon Weight:	8.33 lb	Boiling Range:	259-368°F
% Solids by Weight:	31.3	H: 2 F: 3 R: 0	
% Solids by Volume:	22.7	Flash Point:	77°F
V.O.C LE:	5.72 lb gal	OSHA Storage:	1B
V.O.C AP:	5.72 lb gal		

**Product Code: Pro-Spray PB-783-2 RED PEARL**

Polyester resin A, N-Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), Iron Oxide (5-10%).

Gallon Weight:	8.35 lb	Boiling Range:	259-368°F
% Solids by Weight:	31.3	H: 2 F: 3 R: 0	
% Solids by Volume:	22.5	Flash Point:	77°F
V.O.C LE:	5.73 lb gal	OSHA Storage:	1B
V.O.C AP:	5.73 lb gal		

**Product Code: Pro-Spray PB-784-2 PEARL GOLD**

Polyester resin A, N-Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), .

Gallon Weight:	8.58 lb	Boiling Range:	259-368°F
% Solids by Weight:	34.5	H: 2 F: 3 R: 0	
% Solids by Volume:	24.1	Flash Point:	77°F
V.O.C LE:	5.62 lb gal	OSHA Storage:	1B
V.O.C AP:	5.62 lb gal		

**Product Code: Pro-Spray PB-785-2 COPPER PEARL**

Polyester resin A, N-Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), Iron Oxide (5-10%)

Gallon Weight:	8.38 lb	Boiling Range:	259-368°F
% Solids by Weight:	32.3	H: 2 F: 3 R: 0	
% Solids by Volume:	23.4	Flash Point:	77°F
V.O.C LE:	5.67 lb gal	OSHA Storage:	1B
V.O.C AP:	5.67 lb gal		

**Product Code: Pro-Spray PB-786-2 PEARL WHITE ULTRAFINE**

Polyester resin A, N-Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%).

Gallon Weight:	8.35 lb	Boiling Range:	259-368°F
% Solids by Weight:	31.5	H: 2 F: 3 R: 0	
% Solids by Volume:	22.7	Flash Point:	77°F
V.O.C LE:	5.72 lb gal	OSHA Storage:	1B
V.O.C AP:	5.72 lb gal		

**Product Code: Pro-Spray PB-787-2 PEARL RED FINE**

Polyester resin A, N-Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), Rutile (5-10%).

Gallon Weight:	8.36 lb	Boiling Range:	259-368°F
% Solids by Weight:	31.3	H: 2 F: 3 R: 0	
% Solids by Volume:	22.4	Flash Point:	77°F
V.O.C LE:	5.74 lb gal	OSHA Storage:	1B
V.O.C AP:	5.74 lb gal		

**Product Code: Pro-Spray PB-788-2 RUSSET PEARL FINE**

Polyester resin A, N-Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), Iron Oxide (5-10%), .

Gallon Weight:	8.39 lb	Boiling Range:	259-368°F
% Solids by Weight:	32.3	H: 2 F: 3 R: 0	
% Solids by Volume:	23.3	Flash Point:	77°F
V.O.C LE:	5.68 lb gal	OSHA Storage:	1B
V.O.C AP:	5.68 lb gal		

**Product Code: Pro-Spray PB-789-2 PEARL BLUE FINE**

Polyester resin A, N-Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), tin oxide, rutile.

Gallon Weight:	8.41 lb	Boiling Range:	259-368°F
% Solids by Weight:	32.4	H: 2 F: 3 R: 0	
% Solids by Volume:	23.2	Flash Point:	77°F
V.O.C LE:	5.69 lb gal	OSHA Storage:	1B
V.O.C AP:	5.69 lb gal		

**Product Code: Pro-Spray PB-790-2 PEARL VIOLET MEDIUM**

Polyester resin A, N-Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), titanium oxide.

Gallon Weight:	8.43 lb	Boiling Range:	259-368°F
% Solids by Weight:	33.0	H: 2 F: 3 R: 0	
% Solids by Volume:	23.7	Flash Point:	77°F
V.O.C LE:	5.65 lb gal	OSHA Storage:	1B
V.O.C AP:	5.65 lb gal		

**Product Code: Pro-Spray PB-791-2 PEARL GREEN MEDIUM**

Polyester resin A, N-Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), rutile, .

Gallon Weight:	8.42 lb	Boiling Range:	259-368°F
% Solids by Weight:	32.6	H: 2 F: 3 R: 0	
% Solids by Volume:	22.30	Flash Point:	70°F
V.O.C LE:	5.67 lb gal	OSHA Storage:	1B

V.O.C AP: 5.67 lb gal

**Product Code: Pro-Spray PB-792-2 H.S. BLUE FROST**

Polyester resin A, N-Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), titanium oxide.

Gallon Weight:	8.03 lb	Boiling Range:	259-368°F
% Solids by Weight:	29.4	H: 2 F: 3 R: 0	
% Solids by Volume:	23.4	Flash Point:	79°F
V.O.C LE:	5.67 lb gal	OSHA Storage:	1B
V.O.C AP:	5.67 lb gal		

**Product Code: Pro-Spray PB-793-2 GRAPHITE FLAKE**

Polyester resin A, N-Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Graphite (1-5%).

Gallon Weight:	8.06 lb	Boiling Range:	259-368°F
% Solids by Weight:	29.4	H: 2 F: 3 R: 0	
% Solids by Volume:	23.1	Flash Point:	77°F
V.O.C LE:	5.69 lb gal	OSHA Storage:	1B
V.O.C AP:	5.69 lb gal		

**Product Code: Pro-Spray PB-794-2 GOLD FLASH**

Polyester resin A, N-Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Iron Oxide (1-5%), Aluminium (5-10%)

Gallon Weight:	8.35 lb	Boiling Range:	259-368°F
% Solids by Weight:	32.98	H: 2 F: 3 R: 0	
% Solids by Volume:	24.4	Flash Point:	77°F
V.O.C LE:	5.59 lb gal	OSHA Storage:	1B
V.O.C AP:	5.59 lb gal		

**Product Code: Pro-Spray PB-795-2 ORANGE ALUMINIUM**

Polyester resin A, N-Butyl Acetate, Xylene (7.4%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, Naptha (Petroleum), Hydrotreated heavy, n.butyl alcohol, Cellulose Acetate Butyrate (7.5-10%), Aluminium (1-5%).

Gallon Weight:	8.01 lb	Boiling Range:	226-401°F
% Solids by Weight:	28.17	H: 2 F: 3 R: 0	
% Solids by Volume:	19.9	Flash Point:	73°F
V.O.C LE:	5.75 lb gal	OSHA Storage:	1B
V.O.C AP:	5.75 lb gal		

**Product Code: Pro-Spray PB-796-2 SUPER ORANGE PEARL**

Polyester resin A, N-Butyl Acetate, Xylene (7.2%), solvent naphtha (petroleum), light aromatic, 1,2,4-Trimethylbenzene, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Cellulose Acetate Butyrate (5-10%), Titanium Dioxide, Mica, Tin Oxide.

Gallon Weight:	8.44 lb	Boiling Range:	259-368°F
% Solids by Weight:	36.14	H: 2 F: 3 R: 0	
% Solids by Volume:	25.1	Flash Point:	77°F
V.O.C LE:	5.39 lb gal	OSHA Storage:	1B
V.O.C AP:	5.39 lb gal		

**Product Code: Pro-Spray PSE-1001-18 CRYSTAL SILVER**

Polyester resin A, N-Butyl Acetate, Xylene (15-25%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Cellulose Acetate Butyrate (5-10%), Aluminium oxide, Titanium dioxide, Tin oxide.

Gallon Weight:	8.64 lb	Boiling Range:	259-368°F
% Solids by Weight:	35.2	H: 2 F: 3 R: 0	
% Solids by Volume:	24.4	Flash Point:	77°F
V.O.C LE:	5.59 lb gal	OSHA Storage:	1B
V.O.C AP:	5.59 lb gal		

**Product Code: Pro-Spray PSE-1002-18 SUNBEAM GOLD**

Polyester resin A, N-Butyl Acetate, Xylene (15-25%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Cellulose Acetate Butyrate (5-10%), Aluminium oxide, Titanium dioxide, Tin oxide.

Gallon Weight:	8.63 lb	Boiling Range:	259-368°F
% Solids by Weight:	35.0	H: 2 F: 3 R: 0	
% Solids by Volume:	24.2	Flash Point:	77°F
V.O.C LE:	5.61 lb gal	OSHA Storage:	1B
V.O.C AP:	5.61 lb gal		

**Product Code: Pro-Spray PSE-1003-18 RADIANT RED**

Polyester resin A, N-Butyl Acetate, Xylene (15-25%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Cellulose Acetate Butyrate (5-10%), Aluminium oxide, Iron oxide.

Gallon Weight:	8.51 lb	Boiling Range:	259-368°F
% Solids by Weight:	33.7	H: 2 F: 3 R: 0	
% Solids by Volume:	23.8	Flash Point:	77°F
V.O.C LE:	5.64 lb gal	OSHA Storage:	1B
V.O.C AP:	5.64 lb gal		

**Product Code: Pro-Spray PSE-1004-18 GALAXY BLUE**

Polyester resin A, N-Butyl Acetate, Xylene (15-25%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Cellulose Acetate Butyrate (5-10%), Aluminium oxide, Titanium dioxide, Tin oxide.

Gallon Weight:	8.56 lb	Boiling Range:	259-368°F
% Solids by Weight:	34.49	H: 2 F: 3 R: 0	

% Solids by Volume:	24.3	Flash Point:	77°F
V.O.C LE:	5.6 lb gal	OSHA Storage:	1B
V.O.C AP:	5.6 lb gal		

**Product Code: Pro-Spray PSE-1005-18 STELLAR GREEN**

Polyester resin A, N-Butyl Acetate, Xylene (15-25%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Cellulose Acetate Butyrate (5-10%), Aluminium oxide, Titanium dioxide, Tin oxide.

Gallon Weight:	8.51 lb	Boiling Range:	259-368°F
% Solids by Weight:	34.52	H: 2 F: 3 R: 0	
% Solids by Volume:	24.	Flash Point:	77°F
V.O.C LE:	5.58 lb gal	OSHA Storage:	1B
V.O.C AP:	5.58 lb gal		

**Product Code: Pro-Spray PSE-1006-18 SOLARIS RED**

Polyester resin A, N-Butyl Acetate, Xylene (15-25%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Cellulose Acetate Butyrate (5-10%), Aluminium oxide, Titanium dioxide, Tin oxide.

Gallon Weight:	8.59 lb	Boiling Range:	259-368°F
% Solids by Weight:	34.71	H: 2 F: 3 R: 0	
% Solids by Volume:	24.1	Flash Point:	77°F
V.O.C LE:	5.61 lb gal	OSHA Storage:	1B
V.O.C AP:	5.61 lb gal		

**Product Code: Pro-Spray PSE-1007-18 FIRESIDE COPPER**

Polyester resin A, N-Butyl Acetate, Xylene (15-25%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Cellulose Acetate Butyrate (5-10%), Aluminium oxide, Iron oxide.

Gallon Weight:	8.59 lb	Boiling Range:	259-368°F
% Solids by Weight:	34.5	H: 2 F: 3 R: 0	
% Solids by Volume:	23.8	Flash Point:	77°F
V.O.C LE:	5.62 lb gal	OSHA Storage:	1B
V.O.C AP:	5.62 lb gal		

**Product Code: Pro-Spray PSE-1010-18 VIOLA FANTASY**

Polyester resin A, N-Butyl Acetate, Xylene (8.4%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Propylene glycol monomethyl ether, Cellulose Acetate Butyrate (7.5-12.5%), Silica, Titanium Dioxide, Tin Oxide, Zirconium Oxide.

Gallon Weight:	8.35 lb	Boiling Range:	199-390°F
% Solids by Weight:	35.56	H: 2 F: 3 R: 0	
% Solids by Volume:	25.2	Flash Point:	75°F
V.O.C LE:	5.38 lb gal	OSHA Storage:	1B
V.O.C AP:	5.38 lb gal		

**Product Code: Pro-Spray PSE-1011-18 ARCTIC FIRE**

Polyester resin A, N-Butyl Acetate, Xylene (8.4%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Isobutyl alcohol, Propylene glycol monomethyl ether, Cellulose Acetate Butyrate (7.5-12.5%), Silica, Titanium Dioxide, Tin Oxide, Zirconium Oxide.

Gallon Weight:	8.33 lb	Boiling Range:	199-390°F
% Solids by Weight:	34.38	H: 2 F: 3 R: 0	
% Solids by Volume:	26.5	Flash Point:	75°F
V.O.C LE:	5.52 lb gal	OSHA Storage:	1B
V.O.C AP:	5.52 lb gal		

**Product Code: Pro-Spray PSE-1012-18 TROPIC SUNRISE**

Polyester resin A, N-Butyl Acetate, Xylene (8.4%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Isobutyl alcohol, Propylene glycol monomethyl ether, Cellulose Acetate Butyrate (7.5-12.5%), Silica, Titanium Dioxide, Tin Oxide, Zirconium Oxide.

Gallon Weight:	8.36 lb	Boiling Range:	199-390°F
% Solids by Weight:	34.85	H: 2 F: 3 R: 0	
% Solids by Volume:	26.7	Flash Point:	75°F
V.O.C LE:	5.54 lb gal	OSHA Storage:	1B
V.O.C AP:	5.54 lb gal		

**Product Code: Pro-Spray PSE-1013-18 AUTUMN MYSTERY**

Polyester resin A, N-Butyl Acetate, Xylene (8.4%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Propylene glycol monomethyl ether, Cellulose Acetate Butyrate (7.5-12.5%), Silica, Iron oxide, Zirconium Oxide.

Gallon Weight:	8.33 lb	Boiling Range:	199-390°F
% Solids by Weight:	34.21	H: 2 F: 3 R: 0	
% Solids by Volume:	26.6	Flash Point:	75°F
V.O.C LE:	5.48 lb gal	OSHA Storage:	1B
V.O.C AP:	5.48 lb gal		

**Product Code: Pro-Spray PSE-3001-18 SILVER TO GREEN**

Polyester resin A, N-Butyl Acetate, Xylene (7.6%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Propylene glycol monomethyl ether, Cellulose Acetate Butyrate (5-10%), Aluminium, Magnesium fluoride mixture, Propylene glycol n-propyl ether, Chromium.

Gallon Weight:	8.15 lb	Boiling Range:	226-401°F
% Solids by Weight:	28.86	H: 3* F: 3 R: 0	
% Solids by Volume:	21.7	Flash Point:	77°F
V.O.C LE:	5.8 lb gal	OSHA Storage:	1B
V.O.C AP:	5.8 lb gal		

**Product Code: Pro-Spray PSE-3002-18 GOLD TO SILVER**

Polyester resin A, N-Butyl Acetate, Xylene (7.6%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Propylene glycol monomethyl ether, Cellulose Acetate Butyrate (5-10%), Aluminium, Magnesium fluoride mixture, Propylene glycol n-propyl ether, Chromium.

Gallon Weight:	8.2 lb	Boiling Range:	226-401°F
% Solids by Weight:	29.3	H: 3* F: 3 R: 0	
% Solids by Volume:	21.7	Flash Point:	77°F
V.O.C LE:	5.8 lb gal	OSHA Storage:	1B
V.O.C AP:	5.8 lb gal		

**Product Code: Pro-Spray PSE-3003-18 GREEN TO PURPLE**

Polyester resin A, N-Butyl Acetate, Xylene (7.6%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Propylene glycol monomethyl ether, Cellulose Acetate Butyrate (5-10%), Aluminium, Magnesium fluoride mixture, Propylene glycol n-propyl ether, Chromium.

Gallon Weight:	8.14 lb	Boiling Range:	226-401°F
% Solids by Weight:	29.44	H: 3* F: 3 R: 0	
% Solids by Volume:	22.5	Flash Point:	77°F
V.O.C LE:	5.74 lb gal	OSHA Storage:	1B
V.O.C AP:	5.74 lb gal		

**Product Code: Pro-Spray PSE-3004-18 CYAN TO PURPLE**

Polyester resin A, N-Butyl Acetate, Xylene (7.6%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Propylene glycol monomethyl ether, Cellulose Acetate Butyrate (5-10%), Aluminium, Magnesium fluoride mixture, Propylene glycol n-propyl ether, Chromium.

Gallon Weight:	8.23 lb	Boiling Range:	226-401°F
% Solids by Weight:	30.73	H: 3* F: 3 R: 0	
% Solids by Volume:	23.1	Flash Point:	77°F
V.O.C LE:	5.7 lb gal	OSHA Storage:	1B
V.O.C AP:	5.7 lb gal		

**Product Code: Pro-Spray PSE-3005-18 BLUE TO RED**

Polyester resin A, N-Butyl Acetate, Xylene (7.6%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Propylene glycol monomethyl ether, Cellulose Acetate Butyrate (5-10%), Aluminium, Magnesium fluoride mixture, Propylene glycol n-propyl ether, Chromium.

Gallon Weight:	8.16 lb	Boiling Range:	226-401°F
% Solids by Weight:	29.96	H: 3* F: 3 R: 0	
% Solids by Volume:	22.9	Flash Point:	77°F
V.O.C LE:	5.72 lb gal	OSHA Storage:	1B
V.O.C AP:	5.72 lb gal		

**Product Code: Pro-Spray PSE-3006-18 MAGENTA TO GOLD**

Polyester resin A, N-Butyl Acetate, Xylene (7.6%), solvent naphtha (petroleum), light aromatic, Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Propylene glycol monomethyl ether, Cellulose Acetate Butyrate (5-10%), Aluminium, Magnesium fluoride mixture, Propylene glycol n-propyl ether, Chromium.

Gallon Weight:	8.20 lb	Boiling Range:	226-401°F
% Solids by Weight:	30.24	H: 3* F: 3 R: 0	
% Solids by Volume:	22.9	Flash Point:	77°F
V.O.C LE:	5.72 lb gal	OSHA Storage:	1B
V.O.C AP:	5.72 lb gal		

**Product Code: Pro-Spray VB-602-2 BRIGHT MAROON V.H.S.**

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (10%), Cellulose Acetate Butyrate (5-10%), C.I. Pigment Red 224 (5-10%)

Gallon Weight:	8.25 lb	Boiling Range:	259-418°F
% Solids by Weight:	27.8	H: 2 F: 3 R: 0	
% Solids by Volume:	18.6	Flash Point:	70°F
V.O.C LE:	5.96 lb gal	OSHA Storage:	1B
V.O.C AP:	5.96 lb gal		

**Product Code: Pro-Spray VB-604-2 PALE YELLOW**

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (10%), C.I. Pigment Yellow 184 (Bismuth vanadium tetraoxide) (5-10%).

Gallon Weight:	9.52 lb	Boiling Range:	259-418°F
% Solids by Weight:	55.7	H: 2 F: 3 R: 0	
% Solids by Volume:	42.4	Flash Point:	70°F
V.O.C LE:	4.22 lb gal	OSHA Storage:	1B
V.O.C AP:	4.22 lb gal		

**Product Code: Pro-Spray VB-605-2 BASECOAT JET BLACK**

Polyester Resin C, ethyl benzene, N-Butyl Acetate, Xylene (10.1%), Propylene glycol monomethyl ether acetate, Cellulose Acetate Butyrate (5-10%), Carbon Black (1-5%), Butyl Benzyl Phthalate (0.5-1%).

Gallon Weight:	8.11 lb	Boiling Range:	199-390°F
% Solids by Weight:	25.36	H: 2 F: 3 R: 0	
% Solids by Volume:	18.4	Flash Point:	80°F
V.O.C LE:	6.05 lb gal	OSHA Storage:	1B
V.O.C AP:	6.05 lb gal		

**Product Code: Pro-Spray VB-606-2 ORANGE RED**

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (10%), monoazo orange (10-20%).  
 Gallon Weight: 8.56 lb Boiling Range: 259-418°F  
 % Solids by Weight: 43.5 H: 2 F: 3 R: 0  
 % Solids by Volume: 34.0 Flash Point: 70°F  
 V.O.C LE: 4.83 lb gal OSHA Storage: 1B  
 V.O.C AP: 4.83 lb gal

**Product Code: Pro-Spray VB-610-2 MID YELLOW**

Hydroxy Acrylic Resin A, N-Butyl Acetate (20-30%), Propylene glycol monomethyl ether acetate (10-20%), Ethylene Glycol Monobutyl Ether (1-10%), Yellow (5-10%).  
 Gallon Weight: 10.40 lb Boiling Range: 259-418°F  
 % Solids by Weight: 59.1 H: 2 F: 3 R: 0  
 % Solids by Volume: 43.9 Flash Point: 70°F  
 V.O.C LE: 4.11 lb gal OSHA Storage: 1B  
 V.O.C AP: 4.11 lb gal

**Product Code: Pro-Spray VB-618-2 YELLOW**

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (10%), yellow benzimidazolone (5-10%).  
 Gallon Weight: 8.71 lb Boiling Range: 259-418°F  
 % Solids by Weight: 50.2 H: 2 F: 3 R: 0  
 % Solids by Volume: 40.7 Flash Point: 70°F  
 V.O.C LE: 4.34 lb gal OSHA Storage: 1B  
 V.O.C AP: 4.34 lb gal

**Product Code: Pro-Spray VB-619-2 H.S. PURE MAGENTA**

Hydroxy Acrylic Resin B, N-Butyl Acetate, Xylene (10-20%), Propylene glycol monomethyl ether acetate (1-5%), N-Butyl Alcohol (1-5%), Cellulose Acetate Butyrate (1-5%), Quinacridone (0-5%)  
 Gallon Weight: 8.69 lb Boiling Range: 259-418°F  
 % Solids by Weight: 31.0 H: 2 F: 3 R: 0  
 % Solids by Volume: 24.7 Flash Point: 70°F  
 V.O.C LE: 5.52 lb gal OSHA Storage: 1B  
 V.O.C AP: 5.52 lb gal

**Product Code: Pro-Spray VB-620-2 H.S. RED VIOLET**

Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, ethyl benzene, Xylene (10%), Quinacridone (10-20%)  
 Gallon Weight: 8.69 lb Boiling Range: 259-368°F  
 % Solids by Weight: 46.6 H: 2 F: 3 R: 0  
 % Solids by Volume: 36.6 Flash Point: 82°F  
 V.O.C LE: 4.64 lb gal OSHA Storage: 1B  
 V.O.C AP: 4.64 lb gal

**Product Code: Pro-Spray VB-624-2 H.S. SPEED RED**

Hydroxy Acrylic Resin B, Cellulose Acetate Butyrate (5-10%), Propylene glycol monomethyl ether acetate, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, ethyl benzene, Xylene (10%), Pigment Red 254 (10-20%).  
 Gallon Weight: 8.81 lb Boiling Range: 259-368°F  
 % Solids by Weight: 49.2 H: 2 F: 3 R: 0  
 % Solids by Volume: 38.8 Flash Point: 82°F  
 V.O.C LE: 4.48 lb gal OSHA Storage: 1B  
 V.O.C AP: 4.48 lb gal

**Product Code: Pro-Spray 400-3 H.S PLUS SUPER WHITE**

Hydroxy Acrylic Resin C, Polyester Resin A, N-Butyl Acetate, Methyl isoamyl Ketone, Titanium Dioxide (20-30%), silica, aluminium hydroxide.  
 Gallon Weight: 12.20 lb Boiling Range: 259-418°F  
 % Solids by Weight: 79.0 H: 2 F: 3 R: 0  
 % Solids by Volume: 65.0 Flash Point: 70°F  
 V.O.C LE: 2.56 lb gal OSHA Storage: 1B  
 V.O.C AP: 2.56 lb gal

**Product Code: Pro-Spray SCB-673-3 SINGLE LAYER ADJUSTER**

Acrylic Resin A, Acrylic Resin B, N-Butyl Acetate, Xylene (2%), Solvent naphtha (petroleum) light aromatic.  
 Gallon Weight: 8.20 lb Boiling Range: 259-418°F  
 % Solids by Weight: 48.0 H: 2 F: 3 R: 0  
 % Solids by Volume: 41.2 Flash Point: 77°F  
 V.O.C LE: 4.27 lb gal OSHA Storage: 1B  
 V.O.C AP: 4.27 lb gal

**Product Code: Pro-Spray SCB-408-3 SINGLE LAYER BINDER**

Acrylic Resin A, Acrylic Resin B, N-Butyl Acetate, Xylene (2%), Solvent naphtha (petroleum) light aromatic.  
 Gallon Weight: 8.20 lb Boiling Range: 259-418°F  
 % Solids by Weight: 48.0 H: 2 F: 3 R: 0  
 % Solids by Volume: 41.2 Flash Point: 77°F  
 V.O.C LE: 4.27 lb gal OSHA Storage: 1B  
 V.O.C AP: 4.27 lb gal

**Product Code: Pro-Spray BCB-005-3 BASECOAT FLIP CONTROL**

Acrylic Polymer A, Polyester resin A, Xylene (20-30%), N-Butyl Acetate, Propylene glycol monomethyl ether acetate, Cellulose Acetate Butyrate, Wax Dispersion.

Gallon Weight:	7.75 lb	Boiling Range	259-295°F
% Solids by Weight:	17.0	H: 2 F: 3 R: 0	
% Solids by Volume:	13.6	Flash Point	70°F
V.O.C LE:	6.43 lb gal	OSHA Storage:	1B
V.O.C AP:	6.43 lb gal		

**Product Code: Pro-Spray BCB-600-3, -5 BASECOAT BALANCER**

Acrylic Polymer A, Polyester resin A, Xylene (20-30%), N-Butyl Acetate, Propylene glycol monomethyl ether acetate, Cellulose Acetate Butyrate, Wax Dispersion.

Gallon Weight:	7.94 lb	Boiling Range	259-295°F
% Solids by Weight:	26.1	H: 2 F: 3 R: 0	
% Solids by Volume:	20.9	Flash Point	70°F
V.O.C LE:	5.86 lb gal	OSHA Storage:	1B
V.O.C AP:	5.86 lb gal		

**Product Code: Pro-Spray BCB-825-3 BASECOAT FLIP CONTROL H.S.**

Hydroxy Acrylic Resin, Acrylic Resin, Solvent naphtha (petroleum) light aromatic, Xylene (10-20%), N-Butyl Acetate, Propylene glycol monomethyl ether acetate, Wax Dispersion.

Gallon Weight:	7.97 lb	Boiling Range	259-418°F
% Solids by Weight:	30.1	H: F: R:	
% Solids by Volume:	24.8	Flash Point:	70°F
V.O.C LE:	5.57 lb gal	OSHA Storage:	1B
V.O.C AP:	5.57 lb gal		

**Product Code: Pro-Spray SCBC-574-3 SOLID COLOR BASECOAT CONVERTER**

Acrylic Polymer A, Xylene (5-10%), N-Butyl Acetate, Propylene glycol monomethyl ether acetate, Cellulose Acetate Butyrate, Silica,

Gallon Weight:	8.23 lb	Boiling Range:	176-295°F
% Solids by Weight:	31.8	H: 2 F: 3 R: 0	
% Solids by Volume:	26.3	Flash Point	70°F
V.O.C LE:	5.61 lb gal	OSHA Storage:	1B
V.O.C AP:	5.61 lb gal		

**Product Code: Pro-Spray BCB-35005-3 LOW VOC BASECOAT FLIP CONTROL**

Polyester resin F (10-20%), Parachlorobenzotrifluoride (40-50%), N-Butyl Acetate (1-5%), Cellulose Acetate Butyrate (5-10%), Acetone (20-25%), Ethyl 3-Ethoxy 3-Ethoxy Propionate (5-10%), Hydrophobic fumed silica treated with Dimethylchlorosilina (1-5%), Methyl Isoamyl Ketone (5-10%)

Gallon Weight:	9.04 lb	Boiling Range	132-300°F
% Solids by Weight:	23.7	H: 2 F: 3 R: 0	
% Solids by Volume:	N/E	Flash Point	0°F
V.O.C LE:	3.52 lb gal	OSHA Storage:	1B
V.O.C AP:	6.90 lb gal		

**Product Code: Pro-Spray BCB-35600-3 LOW VOC BASECOAT BALANCER**

Polyester resin F (20-30%), Parachlorobenzotrifluoride (20-25%), Acetone (15-20%), N-Butyl Acetate (5-10%), Cellulose Acetate Butyrate (5-10%), Hydrophobic fumed silica treated with Dimethylchlorosilina (0.5-1.5%) , Methyl Isoamyl Ketone (1-5%)

Gallon Weight:	9.04 lb	Boiling Range	132-300°F
% Solids by Weight:	33.45	H: 2 F: 3 R: 0	
% Solids by Volume:	N/E	Flash Point	0°F
V.O.C LE:	1.96 lb gal	OSHA Storage:	1B
V.O.C AP:	6.02 lb gal		

**Product Code: Pro-Spray BCB-35825-3 LOW VOC BASECOAT FLIP CONTROL H.S.**

Polyester Resin F (15-20%), Parachlorobenzotrifluoride (30-35%), Acetone (20-25%), Cellulose Acetate Butyrate (10-20%), N-Butyl Acetate (1-5%), Methyl Isoamyl Ketone (1-5%).

Gallon Weight:	8.78 lb	Boiling Range	132-300°F
% Solids by Weight:	35.41	H:2 F:3 R:0	
% Solids by Volume:	N/E	Flash Point:	0°F
V.O.C LE:	1.93 lb gal	OSHA Storage:	1B
V.O.C AP:	5.68 lb gal		

**Product Code: Pro-Spray SCBC-35574-3 LOW VOC SOLID COLOR BASECOAT CONVERTER**

Polyester resin F (10-20%), Methyl Isoamyl Ketone (15-25%), Parachlorobenzotrifluoride (25-30%), N-Butyl Acetate (1-5%), Cellulose Acetate Butyrate (10-20%), Propylene glycol monomethyl ether acetate (5-10%), Ethyl 3-Ethoxy Propionate (15-25%).

Gallon Weight:	9.08 lb	Boiling Range:	132-300°F
% Solids by Weight:	27.76	H: 2 F: 3 R: 0	
% Solids by Volume:	N/E	Flash Point	77°F
V.O.C LE:	5.21 lb gal	OSHA Storage:	1C
V.O.C AP:	6.56 lb gal		

**Product Code: Pro-Spray A-380-2 MATTING AGENT**

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N-Butyl Acetate, Xylene (5-10%), Synthetic amorphous silica (10-20%)

Gallon Weight:	8.82 lb	Boiling Range:	259-418°F
% Solids by Weight:	40.3	H: 2 F: 3 R: 0	
% Solids by Volume:	28.0	Flash Point:	70°F
V.O.C LE:	5.27 lb gal	OSHA Storage:	1B
V.O.C AP:	5.27 lb gal		

**Product Code: Pro-Spray P-526-2 TEXTURE ADDITIVE FINE**

Hydroxy Acrylic Resin A, Polyester Resin, nylon, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Xylene (10%).  
 Gallon Weight: 8.52 lb Boiling Range: 259-418°F  
 % Solids by Weight: 66.94 H: 2 F: 3 R: 0  
 % Solids by Volume: 61.5 Flash Point: 73°F  
 V.O.C LE: 2.81 lb gal OSHA Storage: 1B  
 V.O.C AP: 2.81 lb gal

**Product Code: Pro-Spray P-528-2 TEXTURE ADDITIVE COARSE**

Hydroxy Acrylic Resin A, Polyester Resin, nylon, solvent naphtha (petroleum), light aromatic, N-Butyl Acetate, Xylene (10%).  
 Gallon Weight: 8.60 lb Boiling Range: 259-418°F  
 % Solids by Weight: 67.38 H: 2 F: 3 R: 0  
 % Solids by Volume: 61.7 Flash Point: 73°F  
 V.O.C LE: 2.80 lb gal OSHA Storage: 1B  
 V.O.C AP: 2.80 lb gal

**Product Code: Pro-Spray P-2020-2 PLASTICIZING ADDITIVE**

Polyester Resin, N-Butyl Acetate, Xylene (2%), Solvent naphtha (petroleum) light aromatic.  
 Gallon Weight: 8.47 lb Boiling Range: 259-418°F  
 % Solids by Weight: 54.7 H: 2 F: 3 R: 0  
 % Solids by Volume: 47.6 Flash Point: 75°F  
 V.O.C LE: 3.84 lb gal OSHA Storage: 1B  
 V.O.C AP: 3.84 lb gal

**Product Code: Pro-Spray EBB-20-3 ENGINE BAY BINDER**

Hydroxy acrylic Polymer A, N-Butyl Acetate, Xylene (5%), Titanium Dioxide, calcium carbonate, Barium sulfate.  
 Gallon Weight: 12.59 lb Solvent Density: heavier than air  
 % Solids by Weight: 71.6 H: 2 F: 3 R: 0  
 % Solids by Volume: 51.1 Flash Point: 70°F  
 V.O.C LE: 3.58 lb gal OSHA Storage: 1B  
 V.O.C AP: 3.58 lb gal

**Product Code: Pro-Spray EBA-50-3 ENGINE BAY ADJUSTER**

Hydroxy acrylic Polymer A, N-Butyl Acetate, Xylene (5%), Titanium Dioxide, calcium carbonate, Barium sulfate.  
 Gallon Weight: 10.67 lb Solvent Density: heavier than air  
 % Solids by Weight: 63.2 H: 2 F: 3 R: 0  
 % Solids by Volume: 46.3 Flash Point: 70°F  
 V.O.C LE: 3.93 lb gal OSHA Storage: 1B  
 V.O.C AP: 3.93 lb gal

**Product Code: Pro-Spray CSS-3500-3 COMPLIANT SINGLE LAYER BINDER**

Acrylic Resin, N-Butyl Acetate, 2-Butoxyethyl Acetate, methyl isoamyl Ketone, Acetone (16.7%).  
 Gallon Weight: 8.26 lb Boiling Range: 259-418°F  
 % Solids by Weight: 58.59 H: 2 F: 3 R: 0  
 % Solids by Volume: 50.9 Flash Point: 77°F  
 V.O.C LE: 2.58 lb gal OSHA Storage: 1B  
 V.O.C AP: 2.04 lb gal

**Product Code: Pro-Spray CSS-3510-3 COMPLIANT SINGLE JET BLACK**

Hydroxy acrylic Polymer A, Acrylic Resin, N-Butyl Acetate, methyl isoamyl Ketone, Carbon Black (1-5%).  
 Gallon Weight: 8.36 lb Boiling Range: 259-418°F  
 % Solids by Weight: 54.5 H: 2 F: 3 R: 0  
 % Solids by Volume: 47.5 Flash Point: 77°F  
 V.O.C LE: 3.80 lb gal OSHA Storage: 1B  
 V.O.C AP: 3.80 lb gal

**Product Code: Pro-Spray P-451-2, P-451-3 BASECOAT JET BLACK**

Polyester resin C, N-Butyl Acetate, Xylene (5-10%), Propylene glycol monomethyl ether acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Carbon Black (1-5%), Formaldehyde, Butyl Benzyl Phthalate (0.1-0.5%).  
 Gallon Weight: 8.10 lb Boiling Range: 259-418°F  
 % Solids by Weight: 28.21 H: 2 F: 3 R: 0  
 % Solids by Volume: 19.1 Flash Point: 70°F  
 V.O.C LE: 5.82 lb gal OSHA Storage: 1B  
 V.O.C AP: 5.82 lb gal

**Product Code: Pro-Spray BC-452-2, BC-452-3 BASECOAT 1:1 DEEP JET BLACK**

Polyester resin C, N-Butyl Acetate, Xylene (5-10%), Propylene glycol monomethyl ether acetate, ethyl benzene, n.butyl alcohol, Cellulose Acetate Butyrate (10-15%), Carbon Black (1-5%), Formaldehyde, Butyl Benzyl Phthalate (0.1-1%).  
 Gallon Weight: 8.10 lb Boiling Range: 259-418°F  
 % Solids by Weight: 28.21 H: 2 F: 3 R: 0  
 % Solids by Volume: 19.1 Flash Point: 70°F  
 V.O.C LE: 5.82 lb gal OSHA Storage: 1B  
 V.O.C AP: 5.82 lb gal

**Product Code: Pro-Spray A-350 MS BRILLIANT WHITE**

Hydroxy acrylic Polymer A, Polyester resin B, N-Butyl Acetate, Xylene (20-30%), Titanium Dioxide (25-35%).  
 Gallon Weight: 10.77 Boiling Range: 259-418°F  
 % Solids by Weight: 64.95 H: 2 F: 3 R: 0

% Solids by Volume: 48.1  
V.O.C: 3.77 lb gal  
V.O.C less Exempt 3.77 lb gal

Flash Point: 70-90°F  
OSHA Storage: 1B

**Product Code: Pro-Spray A-351 MS JET BLACK**

Hydroxy acrylic Polymer A, Polyester Resin B, N-Butyl Acetate, Xylene (20-30%), Carbon Black (1-5%).  
Gallon Weight: 8.35 Boiling Range: 259-418°F  
% Solids by Weight: 51.29 H: 2 F: 3 R: 0  
% Solids by Volume: 43.3 Flash Point: 70-90°F  
V.O.C: 4.12 lb gal OSHA Storage: 1B  
V.O.C less Exempt 4.12 lb gal

**Product Code: Pro-Spray A-352 MS DIAMOND WHITE**

Hydroxy acrylic Polymer A, Polyester Resin B, N-Butyl Acetate, Xylene (20-30%), Titanium Dioxide (25-30%).  
Gallon Weight: 10.44 Boiling Range: 259-418°F  
% Solids by Weight: 63.53 H: 2 F: 3 R: 0  
% Solids by Volume: 47.6 Flash Point: 70-90°F  
V.O.C: 3.81 lb gal OSHA Storage: 1B  
V.O.C less Exempt 3.81 lb gal